

TECHNICAL DATA SHEET

Product Code:
SPA 7101

Product: GLAZE	
Type: Matt Transparent Frit	
Significative components: SiO ₂ , Al ₂ O ₃ , BaO, CaO, MgO, K ₂ O, Na ₂ O	
FIRING TECHNOLOGY	
ARTISTIC	<input checked="" type="checkbox"/>
SINGLE FIRING	<input checked="" type="checkbox"/>

In any case the result depends on the base employed, temperatures and firing cycle.
Additional information is available in the commercial catalogue and at Colorobbia Italia S.p.A. Customer Assistance Laboratory.
All raw materials have been verified and used only if they comply with control

INDICATIVE PHYSICAL CHEMICAL CHARACTERIZATION		
	METHOD*	
CERAMIC TEST	PAQ 18-111 s;	CONFORM TO THE VISUAL INSPECTION
GRANULOMETRIC TEST	PAQ 18-01s	Residue 45 micron (100cc) from: 0,3 g to: 0,8 g
DILATOMETER**	PAQ 18-21f (50-400 °C)	$\alpha = 86 \times 10^{-7} \text{ } ^\circ\text{C}^{-1}$ Trasformation T. 573 °C Dilatomet. Softening T. N/D °C
HEATING MICROSCOPY**	PAQ 18-22f	Starting Shrinkage T. 1120 °C Shrinkage T. 1210 °C Ball T. 1265 °C Half Ball T. 1280 °C
<p>* PAQ = Colorobbia Italia control procedure code ** Indicative Physical Chemical Characteristic obtained grinding to 45 micron residue < 1,5 % and firing at ball temperature.</p>		

Quality Assurance Manager

Dott.ssa Silvia Masini

